

测试报告

编号 : SHMR110503904

日期 : 2011-06-08

页码 : 1 of 3

富宥铭板股份有限公司 苏州市相城区望亭镇华阳村新华工业园

下列样品由客户提供及确认:

样品名称

电铸贴片 (INLET)

样品编号

SHMR110503903

SGS 参考号

SP110502732

测试要求

盐雾试验, 耐护手霜

收样日期

2011-05-31

测试周期

2011-05-31/2011-06-07

测试结果

请见下页

******* 待续******

通标标准技术服务(上海) 有限公司授权签名

授权签字人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions. http://www.sgs.com/terms_and_conditions. http.//www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, independent on any invariant of the initiation of liability, independent on any invariant of the initiation of liability, independent on any invariant of the initiation of liability, independent on any invariant of the initiation of liability in the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from references in all the initiation of the initiation of the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any anauthorized alteration forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unlass otherwise stated the lesults shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SHMR 041746

8th building, No. 69, Block 1159, Kangqiao East Road, Pudong District, Shanghai, China 201319 中国 • 上海 • 上海浦东康桥东路1159弄69号8号楼

t (86-21) 61196300 t (86-21) 61196300

f (86-21) 68183920 f (86-21) 68183920



测试报告

编号 : SHMR110503904

日期 : 2011-06-08

页码 : 2 of 3

样品描述: 银色膜

1. 盐雾试验

测试方法: 客户提供

测试条件:

沉降盐液浓度: (5±1)% NaCl (m/m)

试验箱温度: (35±2)℃

盐雾沉降率: (1.0~2.0)ml/(80cm²·h)

沉降盐液 pH 值 (25℃): 6.5~7.2

暴露时间: 96 小时

测试结果: 无可视变化。

2. 耐护手霜

测试方法: 客户提供

测试条件:

75°C, 90%RH, 24h→25°C, 50%RH, 2h

测试结果:

测试试剂	结果
NIVEA 护手霜	漆层无剥落,无褪色
Atrix cream	漆层无剥落,无褪色

备注: 此报告为英文报告 SHMR110503903 的中文译本,如中英文有差异,概以英文为准。

******* 待续******

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms and conditions. httm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms e-document. htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all them; only and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any snauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SHMR 041747

8th building,No.69,Block 1159,Kangqiao East Road, Pudong District, Shanghai, China 201319 t 中国 - 上海 - 上海浦东康桥东路1159弄69号8号楼 邮编: 201319 t

t (86-21) 61196300 t (86-21) 61196300

f (86-21) 68183920 f (86-21) 68183920



测试报告

: SHMR110503904 编号

日期 : 2011-06-08

页码 : 3 of 3

测试照片:



盐雾试验后



耐护手霜测试后(NIVEA护手霜)



耐护手霜测试后 (Atrix cream)

******报告结束******

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms and conditions. total conditions. https://www.sgs.com/terms e-document into contained hereon reflects the Company's findings at the time of its intercent into contained hereon reflects the Company's findings at the time of its intercent into contained hereon reflects the Company's findings at the time of its intercent into contained hereon reflects the Company's findi

SHMR 041756

8th building,No.69,Block 1159,Kangqiao East Road, Pudong District, Shanghai, China 201319 中国・上海・上海浦东康桥东路1159弄69号8号楼

邮编: 201319

t (86-21) 61196300 t (86-21) 61196300 f (86-21) 68183920 f (86-21) 68183920